



EcoSoya PillarBlend

EcoSoya PillarBlend is a clean-burning, easy to use firm wax requiring multiple pours for larger pillars. Designed for use in container candles, molded candles, votives, tarts, melts, and novelty.

Description

Soy Wax

Label Ingredient Statement

Soy Wax

Product Specifications

Mettler Drop Point	129 °F	AOCS Cc 18-80 °F
Congealing Point	121 °F	AOCS Cc 18-80 °F
Needle Penetration	21	ASTM D 1321-65 1/10MM
Color, Red	3.50 Max (%)	AOCS 13b-45 Units
Melting Temperature	129-140 °F	
Pouring Temperature	155-175 °F	
Frangrance Load	12% Max	
Wax Type	Soybean Wax Flakes	
Characteristics	Clean Burning and easy to use	
Applications	Container Candles, Tarts, Melts, & Novelty	
Prop 65 Warning Required	No	

General Guidelines

- Heat wax to temerature between 150°F - 160°F
- Add fragrace and dye, then stir thoroughly.
- Lower pouring temperature between 155°F - 175°F, then pour candles slowly.
- Allow candle to cool as slowly as possible. DO NOT place in a water bath or refrigerator to accelerate the cooling process.

Storage and Shelf Life

12 Months Shelf Life

Store at 75°F or below in a dry and odor free environment

Available Products

Item #	Description	Pack	Net Weight
601035	EcoSoya Pillar Blend Soy Flakes	Carton	45#

Please contact our sales department for samples, pricing, and technical information regarding your specific application or shipment requirements.

Toll-Free – (877) 220-1963
sales@gatewayfoodproducts.com
www.gatewayfoodproducts.com