



EcoSoya Q230

EcoSoya Q230 is extremely clean burning, stable and easy to use. Single pour, pillars may require multiple pours. Smooth re-congealed burn pool.

Designed for use in pillar candles, molded candles, votives, tarts, melts, and novelty.

Description

Soy Wax

Label Ingredient Statement

Soy Wax

Product Specifications

Mettler Drop Point	120 °F	AOCS Cc 18-80 °F
Congealing Point	109 °F	AOCS Cc 18-80 °F
Needle Penetration	29	ASTM D 1321-65 1/10MM
Color, Red	3.50 Max (%)	AOCS 13b-45 Units
Melting Temperature	155-180 °F	
Pouring Temperature	145-175 °F	
Frangrance Load	18% Max	
Wax Type	Soybean Wax Flakes	
Characteristics	Extremely clean burning, stable and easy to use.	
Applications	Pillar Candles, Molded Candles, Votives, Tarts, Melts, and Novelty	
Prop 65 Warning Required	No	

General Guidelines

- Heat wax to temerature between 155°F - 180°F
- Add fragrace and dye, then stir thoroughly
- Lower pouring temperature between 145°F - 175°F, then pour candles slowly.
- Allow candle to cool as slowly as possible. DO NOT place in a water bath or refrigerator to accelerate the cooling process.

Storage and Shelf Life

12 Months Shelf Life

Store at 75°F or below in a dry and odor free environment

Available Products

Item #	Description	Pack	Net Weight
601048	EcoSoya Q230 Soy Flakes	Carton	45#

Please contact our sales department for samples, pricing, and technical information regarding your specific application or shipment requirements.

Toll-Free – (877) 220-1963
sales@gatewayfoodproducts.com
www.gatewayfoodproducts.com